

**DESCRIPTION**

A clear for Waterbased tinters to be added to make coloured basecoats.

**Attributes**

See appropriate clear lacquer datasheet.

**Specification**

Mix ratio:	Ready to use
Viscosity:	Brookfield LV spindle 3 @ 20°C
	Speed 10 33-39 Poise
	Speed 30 13-17 Poise
	Speed 50 8-12 Poise
	Speed 100 4-8 Poise
Non Volatile content:	14-16 %
Gloss:	as topcoat
Specific Gravity:	0.99-1.03
D.F.T:	15-20 µM

**Application**

Substrates:	Aluminium/Steel
Clearcoat:	as specified
Method:	Conventional spray
Flash-off:	5 min. @ 60°C
	40 min. @ 20°C
Curing:	As per clear lacquer

The technical data contained herein is based on our present knowledge and we experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired.

Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application.

Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product.

Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions.

The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.